

LOCTITE[®] PC 7230 L

August 2022

PRODUCT DESCRIPTION

LOCTITE[®] PC 7230 L provides the following product characteristics:

Technology	Epoxy
Chemical Type	Epoxy
Appearance (resin)	Paste grey
Appearance (hardener)	Paste black
Appearance (mixed)	Paste dark grey
Components	Two components – resin & hardener
Mix Ratio, by weight - resin : hardener	3.9 : 1
Mix Ratio, by volume - resin : hardener	4 : 1
Cure	Room temperature cure after mixing
Application	Coating
Application Temperature	15 to 40°C (59 to 104 °F)
Service Temperature (dry)	230°C (446 °F)
Specific Benefits	<ul style="list-style-type: none"> • Ceramic-filled for outstanding resistance to abrasion • Renews worn surfaces fast - reduces downtime • Extends wear life – resists sliding abrasive wear and eliminates costly wear part inventory • Non sag – provides abrasion resistance on overhead and vertical surfaces

LOCTITE[®] PC 7230 L is a two-component ceramic-filled epoxy paste coating that is solvent-free with increased temperature resistance (high temp products). LOCTITE[®] PC 7230 L is designed to protect, rebuild, and repair high wear areas of processing equipment under temperatures from -30 to 230°C (-22 to 446°F). LOCTITE[®] PC 7230 L requires post-curing for ultimate performance and temperature resistance. Typical applications include cyclone and separator bodies, dust collectors and exhausters, pump liners and impellers, fan blades and housings, chutes, and hoppers.

TYPICAL CURING PERFORMANCE

Curing @ 23 °C, 50% RH

Working Time, minutes	30
Cure Time, hours	7

TYPICAL PERFORMANCE OF CURED MATERIAL

Cured for 1 week @ 23°C

Physical Properties

Shore Hardness, Durometer D ISO 868	90
Compressive Strength, ISO 604	N/mm ² 104 (psi) (15,000)

TYPICAL ENVIRONMENTAL RESISTANCE

Dry Service Temperature Resistance, CSA-Z245.20-06/CSA-Z245.21-06 Rating 1, °C	230
Rating 1: cannot be removed cleanly	
Rating 2: less than 50% can be removed	

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions for use

Surface Preparation:

Proper surface preparation is critical to the long-term performance of this product. The exact requirements vary with the severity of the application, expected service life, and initial substrate conditions.

1. Thoroughly clean and abrade surfaces (grit blast if possible), finally clean with LOCTITE SF 7063. The more thorough the degree of surface preparation the better the performance of the application.
2. On vertical or overhead areas, tack welding expanded metal mesh onto the metal substrate is recommended prior to application of LOCTITE[®] PC 7230 L.

Mixing:

1. Measure 4 parts resin to 1 part hardener by volume (3.9 to 1 by weight), transfer entire kit onto a clean and dry mixing surface and mix together until uniform in color.
2. If resin and hardener temperatures are 15°C (59°F) or below, preheat resin only to about 30°C (86°F) but not to exceed 40°C (104°F).

Application:

1. Apply fully mixed material to the prepared surface.
2. Initially apply as a thin film to "wet" out the surface.
3. Build up to desired thickness (minimum 6mm), avoid air entrapment.
4. At 23°C (73°F), the working time is 30 minutes and functional cure time is 7 hours, post cure at 150°C (302°F) for 2 hours.



Coverage:

To achieve a 6 millimeter (0.24 inch) thickness, the coverage rate will be 740 cm² (0.79 ft²) for 10 kg (22 lb), excluding overthickness, repairs, etc.

Repairs:

Any voids, pinholes, low thickness areas found in the coating should be repaired by lightly abrading, cleaning and applying further product.

Clean-up:

Immediately after use clean tools with LOCTITE® solvent base cleaner. Once cured, the material can only be removed mechanically.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: below 8 to 21 °C. Storage greater than 28 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

Product Specification

The technical data contained herein are intended as reference only and are not considered specifications for the product. Product specifications are located on the Certificate of Analysis or please contact Henkel representative.

Approval and Certificate

Please contact a Henkel representative for related approval or certificate of this product.

Data Ranges

The data contained herein may be reported as a typical value. Values are based on actual test data and are verified on a periodic basis.

Temperature/Humidity Ranges: 23 °C / 50% RH = 23±2 °C / 50 ±5% RH

Conversions

(°C x 1.8) + 32 = °F

kV/mm x 25.4 = V/mil

mm / 25.4 = inches

µm / 25.4 = mil

N x 0.225 = lb

N/mm x 5.71 = lb/in

N/mm² x 145 = psi

MPa x 145 = psi

N·m x 8.851 = lb·in

N·m x 0.738 = lb·ft

N·mm x 0.142 = oz·in

mPa·s = cP

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended

applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0

